



## **181 Double Sided Polyester Tape**

### **Product Description:**

Polyester film with an acrylic solvent adhesive.

### **Physical Data:**

Total Thickness (without liner)	205 +/- 5mic
180 Peeling Strength to Steel Plate	>1.8kg/25mm
Initial Tack (steel ball) 14#	>55m
Holding Power	>48 hours
80c Heat Resistance	>30 minutes
120c Heat Resistance	>4 minutes
Temperature	-20 to 120

### **Performance Levels:**

Excellent
Glass, ABS, PVC, UPVC, Foams,
Acrylic
Polycarbonates
Metals
HSE Substrates

### **Storage Conditions**

This product should be stored at room temperature and be kept away from the wet and/or heat source.

It is essential, as with all pressure sensitive tapes, that the surface to which the tape is applied must be clean, dry and free of oil and grease.

### **Additional Product Information:**

The physical characteristics contained in our data sheets represent typical or average values. They do not represent any warranties or guarantees and must not be used for technical specification purposes. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. The buyer is responsible for determining the suitability of the specific tape for its intended use in connection with the users' method of application.



#### **FineCal Distributors**

Temple Trading Estate

Bristol, BS2 0UG

0117 971 1111 [sales@finecal.co.uk](mailto:sales@finecal.co.uk)

[www.finecal.co.uk](http://www.finecal.co.uk)